

Material 94 AU 925

blue

revision index	revision date	page	1 / 3
7	1/12/2016		

Physical properties	nominal range	typical values	
Density DIN EN ISO 1183-1, 23 °C	1.17 ±0.02	1.17	g/cm ³
Hardness DIN ISO 7619-1, Shore A, 23 °C	94 ±3	94	Shore
Hardness DIN ISO 7619-1, Shore D, 23 °C	43 ±5	43	Shore
Modulus 100 %, DIN 53504, S2, 23 °C	> 9	12	MPa
Modulus 300 %, DIN 53504, S2, 23 °C	---	21	MPa
Tensile strength DIN 53504, S2, 23 °C	> 55	64	MPa
Elongation at break DIN 53504, S2, 23 °C	> 430	530	%
Tear strength DIN ISO 34-1, B (b), 23 °C	---	99	KN/m
Compression set DIN ISO 815, 24 h, 100 °C, 20 %	---	35	%
Compression set DIN ISO 815, 70 h, 100 °C, 10 %	---	46	%
Compression set DIN ISO 815, 24 h, 125 °C, 10 %	---	68	%
Low Temperature ISO 11357-2, DSC	---	-40	°C
Torsions pendulum test DIN EN ISO 6721-2A	---	-27	°C
Temperature range	-30°C to 110°C		

Declarations of conformity

	Country	Part	Remark	Expires	unlimited
RoHS conform			including EU 2011/65 and		<input checked="" type="checkbox"/>

Freudenberg

Freudenberg Sealing Technologies
Global Material Technology
Wolfgang Becker
Telefon: +49 (0)6201/80-2893
Fax: +49 (0)6201/88-2893
Email: wolfgang.becker@FST.com

Material
94 AU 925
blue

revision index
7

revision date
1/12/2016

page 2 / 3

Country Part

Remark
EU2015/863 (ROHS III)

Expires unlimited

Freudenberg

Freudenberg Sealing Technologies
Global Material Technology
Wolfgang Becker
Telefon: +49 (0)6201/80-2893
Fax: +49 (0)6201/88-2893
Email: wolfgang.becker@FST.com

Material
94 AU 925

blue

revision index

7

revision date

1/12/2016

page

3 / 3

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg Sealing Technologies

Global Material Technology

Wolfgang Becker

Telefon: +49 (0)6201/80-2893

Fax: +49 (0)6201/88-2893

Email: wolfgang.becker@FST.com